

EVICOM™ GL4/443

Flexible Polyvinyl Chloride

INEOS Compounds

Message:

Specification : BS 7655: Section 4.3: 2000. Type 8 *

Formulated without lead-based additives

* may not be suitable for RF2316 cables

General Information			
Features	Good Flexibility		
	Low (to None) Lead Content		
	Medium Gloss		
Uses	Cable Jacketing		
	Low Temperature Applications		
Appearance	Opaque		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	BS 2782 620A
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	69		BS 2782 365B
BS Softness	54		BS 2782 365A
Cold Bend	-55	°C	BS 2782 151A
Cold Flexibility	-50	°C	BS 2782 150B
Insulation Resistance Constant - K-value (23°C)	0.037	Mohms · km	
Loss of Mass - 7 days (80°C)	0.300	mg/cm ²	BS EN 60811-3-3.2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	15.2	MPa	BS 2782 320A
Tensile Elongation (Break)	310	%	BS 2782 320A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	1.0E+10	ohms · cm	BS 2782 230A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

