

ALTECH® PP-H A 3020/500 GB20

Polypropylene Homopolymer

ALBIS PLASTIC GmbH

Message:

ALTECH®PP-H A 3020/500 GB20 is a polypropylene homopolymer (PP Homopoly) product containing 20% glass beads. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region.

Features include:

Comply with REACH standard

ROHS certification

Homopolymer

General Information			
Filler / Reinforcement	Glass beads, 20% filler by weight		
Features	Homopolymer		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.02	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	10.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2100	MPa	ISO 527-2
Tensile Stress (Break)	20.0	MPa	ISO 527-2
Tensile Strain (Break)	> 20	%	ISO 527-2
Flexural Stress	40.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	27	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	65.0	°C	ISO 75-2/A
Vicat Softening Temperature	100	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature			
Dehumidification desiccant	80 - 120	°C	
Hot air dryer	80 - 120	°C	
Drying Time			
Dehumidification desiccant	2.0 - 3.0	hr	
Hot air dryer	2.0 - 3.0	hr	
Processing (Melt) Temp	200 - 270	°C	
Mold Temperature	20 - 90	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

