

TYNEP® P7408

Polybutylene Terephthalate

Tyne Plastics LLC.

Message:

TYNEP® P7408 is a Polybutylene Terephthalate (PBT) material filled with 40% glass\mineral. It is available in North America.

Important attributes of TYNEP® P7408 are:

Impact Modified

Impact Resistant

General Information			
Filler / Reinforcement	Glass\Mineral,40% Filler by Weight		
Additive	Impact Modifier		
Features	Good Impact Resistance		
	Impact Modified		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	75.8	MPa	ASTM D638
Tensile Elongation (Yield)	2.0	%	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength	117	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	69	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	430	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	193	°C	
1.8 MPa, Unannealed	210	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	6.0E+16	ohms · cm	ASTM D257
Dielectric Strength (1.57 mm, in Air)	30	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	4.00		ASTM D150
Dissipation Factor (1 MHz)	0.020		ASTM D150

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT