

# Huaфон JF-W-AH6046

Polyurethane  
Huaфон Group Co., Ltd.

Message:

Hydrolysis Resistance and High Peeling Strength Type

Characteristics

Mid soft type, high peeling strength, 3 hours hydrolysis resistance at 70°C, flat and nonstick surface, good film property, uniform cell structure, suit for high density technology.

Applications

Shoes

General Information		
Features	Hydrolysis Resistant	
	Non-Stick	
	Soft	
Uses	Footwear	
Additional Information	Nominal Value	Unit
Solvents	DMF	
Uncured Properties	Nominal Value	Unit
Solids Content	31 to 33	%
Viscosity (25°C)	200 to 260	Pa·s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	4.00 to 5.00	MPa
Tensile Strength	> 40.0	MPa
Tensile Elongation at Break	> 500	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

  
WECHAT