

Spartech Polycom PP6928 D88

Polypropylene
Spartech Polycom

Message:

Spartech Polycom PP6928 D88 is a polypropylene product that contains 27% glass \minerals. It is available in North America. Typical application areas are: outdoor applications.
Features include:
Impact modification
high liquidity
Good UV resistance
UV stability

General Information			
Filler / Reinforcement	Glass \mineral, 27% filler by weight		
Additive	Impact modifier UV stabilizer		
Features	Impact modification Good UV resistance High liquidity		
Uses	Outdoor application		
Appearance	White		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	27.6	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield, 23°C	3.0	%	ASTM D638
Fracture, 23°C	5.0	%	ASTM D638
Flexural Modulus - Tangent (23°C)	2280	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	143	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

