Lifoflex® GC 1090

Styrene Ethylene Butylene Styrene Block Copolymer

Müller Kunststoffe GmbH

Message:

The series GA, GB and GC are TPE compounds based on SEBS. They are suited for a lot of different applications and are characterized by an easy processing and high fl exibility.

Properties:

shore hardness: 20 - 90 Shore A different densities: 0,89 - 1,21 g/ccm

translucent, nature colored or direct pigmented materials possible resistant against aqueous solutions, inorganic acids and bases

physiologically harmless

easy processing in injection molding

good adhesion on PP/PE

very good mechanical properties

service temperature range from -40°C up to 100°C

high fl exibility

UV resistant (suitable for outdoor use)

applications with food contact are possible

in conformity with FDA, 10/2011/EC and EN 71/3 (toys)

in conformity with European directives 2002/95/EC (RoHS) and 2003/11/EC

recyclable

Applications:

consumer/household:

sealings for food storage boxes

soft-touch surfaces for packaging

2-component grips for kitchen equipment

toys:

soft seats for sledge

wheels for toy cars

toy characters

electronics:

sealings for housings

soft touch coating for housings

sports and leisure:

bicycle grips

soft-touch grips for hiking and nordic walking sticks

fins

health care:

grips for toothbrushes

sealings and closures for packaging

anti-slip grips for baby tableware

General Information

Features Acid Resistant

Base Resistant

Food Contact Acceptable

Good Adhesion

Good Colorability

Good Flexibility

Good Processability

Good UV Resistance

Low Toxicity

Recyclable Material

Uses	Closures			
	Consumer Applications			
	Electrical/Electronic Applications			
	Flexible Grips			
	Household Goods			
	Medical/Healthcare Applications			
	Outdoor Applications			
	Seals			
	Seats Soft Touch Applications			
				Sporting Goods
	Toothbrush Handles Toys			
				Wheels
	Agency Ratings	EN 71-3		
EU 2003/11/EC				
EU No 10/2011				
FDA Unspecified Rating				
RoHS Compliance	RoHS Compliant			
Appearance	Natural Color			
Physical	Nominal Value	Unit	Test Method	
Density	1.18	g/cm³	ISO 1183/A	
Hardness	Nominal Value	Unit	Test Method	
Shore Hardness (Shore A, 3 sec)	90		DIN 53505	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress - Flow (Yield)	10.5	МРа	DIN 53504	
Tensile Elongation - Flow (Break)	660	%	DIN 53504	
Compression Set			ISO 815	
23°C, 72 hr	45	%		
70°C, 22 hr	60	%		
100°C, 24 hr	72	%		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

