

# Shin-Etsu Elastomer KE-1950-30A/B

Silicone Rubber, HTV

Shin-Etsu Silicones of America

Message:

Shin-Etsu KE-1950-30 is a liquid injection molding silicone. It is supplied as two components which are mixed in a 1:1 ratio to ensure easy and accurate blending. The viscosity of KE-1950-30 is low enough to allow easy pumping through most injection molding systems.

Rapid cure time at elevated temperature.

Long pot life at room temperature.

Typical Applications

O-rings. - Diaphragms.

Capping.

Rubber rollers.

Connector packings.

Other electrical parts

General Information		
Features	Low viscosity	
	Workability, good	
	Fast curing	
Uses	Electrical/Electronic Applications	
	Electrical components	
	Diaphragm	
	Roller	
	Shield	
Agency Ratings	FDA not rated	
	USP Class VI	
Forms	Liquid	
Processing Method	Liquid Injection Molding (LIM)	
Physical	Nominal Value	Unit
Specific Gravity	1.10	g/cm <sup>3</sup>
Hardness	Nominal Value	Unit
Durometer Hardness	32	
Elastomers	Nominal Value	Unit
Tensile Stress (100% Strain)	0.696	MPa
Tensile Strength	8.80	MPa
Tensile Elongation (Break)	700	%
Tear Strength <sup>1</sup>	25.0	kN/m
Compression Set (180°C, 22 hr)	6.0	%
Thermoset	Nominal Value	Unit
Post Cure Time (200°C)	4.0	hr

Additional Information		
Press Cure / Post Cure: Press/Post		
Uncured Properties	Nominal Value	Unit
Curing Time	0.083	hr
NOTE		
1.	B mould	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT