

Magnobond 3347

Epoxy; Epoxide
Magnolia Plastics, Inc.

Message:

Magnobond 3347 is an Epoxy; Epoxide (Epoxy) product. It is available in North America. Typical application: Electrical/Electronic Applications. Primary characteristic: low viscosity.

General Information			
Features	Good Electrical Properties		
	Low Viscosity		
Uses	Electrical/Electronic Applications		
Appearance	Amber		
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	6.8E+16	ohms	ASTM D257
Volume Resistivity	3.3E+16	ohms·cm	ASTM D257
Dielectric Constant (1 kHz)	2.83		ASTM D150
Dissipation Factor			ASTM D150
1 kHz	4.0E-3		
1 MHz	0.015		
Thermoset	Nominal Value	Unit	Test Method
Pot Life (52°C)	22	min	
Thermoset Mix Viscosity	500	cP	ASTM D2393
Demold Time (130°C)	120 to 240	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT