

POLYfill PP EIP8020F

Polypropylene + EPDM Rubber

Polykemi AB

Message:

PP/EPDM Mineral reinforced

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.90 to 1.1	%	
Flow	0.90 to 1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	24.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	5.0	%	
Break	24	%	
Flexural Modulus (23°C)	2100	MPa	ISO 178
Flexural Stress	35.0	MPa	ISO 178
Scratch Resistance - 10 N Fine Structure	3.50	dL	ISO 1518/D65
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	4.0	kJ/m ²	
23°C	12	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-20°C	39	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹			
0.45 MPa, Unannealed	110	°C	ISO 75-2/B
1.8 MPa, Unannealed	58.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	143	°C	ISO 306/A50
--	70.0	°C	ISO 306/B50
CLTE - Flow	6.0E-5 to 8.0E-5	cm/cm/°C	Internal Method
Flammability	Nominal Value	Unit	Test Method
Glow Wire Ignition Temperature (2.00 mm)	750	°C	IEC 60695-2-13

NOTE

1. 120°C/hr

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

