

LNP™ THERMOCOMP™ RF008H compound

Polyamide 66

SABIC Innovative Plastics

Message:

LNP THERMOCOMP RF008H is a compound based on Nylon 66 containing 40% Glass Fiber. Added feature of this grade is: Healthcare.

Also known as: LNP* THERMOCOMP* Compound RF-1008 USS

Product reorder name: RF008H

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Uses	Medical/Healthcare Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.50	g/cm ³	ASTM D792
--	1.47	g/cm ³	ISO 1183
--	1.48	g/cm ³	ASTM D792
Molding Shrinkage			
Flow : 24 hr	0.20 to 0.40	%	ASTM D955
Across Flow : 24 hr	1.0 to 3.0	%	ASTM D955
Flow : 24 hr	0.10 to 0.30	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.60	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.97	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	13300	MPa	ASTM D638
--	12200	MPa	ISO 527-2/1
Tensile Strength			
Break ²	184	MPa	ASTM D638
Break	188	MPa	ISO 527-2/5
Tensile Elongation			
Break ³	2.5	%	ASTM D638
Break	2.7	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁴	10400	MPa	ASTM D790
-- ⁵	12100	MPa	ISO 178
Flexural Stress			
--	287	MPa	ISO 178
Break, 50.0 mm Span ⁶	275	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			
23°C	120	J/m	ASTM D256
23°C ⁷	13	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1100	J/m	ASTM D4812
23°C ⁸	74	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	10.0	J	ASTM D3763
--	3.00	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	252	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁹	> 240	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	2.5E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	2.7E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	5.8E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	5.9E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	282 to 304	°C	
Mold Temperature	93.3 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	1.3 mm/min		
5.	2.0 mm/min		
6.	1.3 mm/min		
7.	80*10*4		
8.	80*10*4		
9.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT