

Pearlthane® 11T92EM

Thermoplastic Polyurethane Elastomer (Polycaprolactone)

Lubrizol Advanced Materials, Inc.

Message:

Pearlthane® 11T92EM is a polycaprolactone copolyester based TPU, supplied in form of translucent, colourless pellets, combining hardness with excellent mechanical properties. It can be extruded and injection-moulded.

Pearlthane® 11T92EM can be extruded into profiles, belts, tubes and film. In the case of injection moulding, this grade is only recommended for certain specific applications, e.g. when large, hard-to-fill mould cavities are used.

General Information			
Features	Medium hardness		
Uses	Films		
	Conveyor belt repair		
	Pipe fittings		
	Profile		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Translucent		
	Colorless		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.16	g/cm ³	ASTM D792
20°C	1.16	g/cm ³	ISO 2781
Moisture Content		%	Internal method
Abrasion Loss	25.0	mm ³	ISO 4649
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	91		ASTM D2240, ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412, ISO 527
100% strain	8.00	MPa	ASTM D412, ISO 527
300% strain	12.0	MPa	ASTM D412, ISO 527
Tensile Strength (Yield)	35.0	MPa	ASTM D412, ISO 527
Tensile Elongation (Break)	600	%	ASTM D412, ISO 527
Tear Strength			
-- ¹	100	kN/m	ASTM D624
--	100	kN/m	ISO 34-1

Compression Set			ASTM D395B
23°C, 70 hr	25	%	ASTM D395B
70°C, 22 hr	43	%	ASTM D395B
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ²	-38.0	°C	ISO 11357-2
Melting Temperature ³	180 - 190	°C	Internal method
Injection	Nominal Value	Unit	
Drying Temperature	100 - 110	°C	
Drying Time	1.0 - 2.0	hr	
Rear Temperature	195	°C	
Middle Temperature	200	°C	
Front Temperature	210	°C	
Nozzle Temperature	210	°C	
Mold Temperature	35.0	°C	
Injection instructions			
Closing force: : 30 tonsScrew diameter: : 30 mmMaximum hydraulic pressure: : 210 barMould: : Plaque 120x120x2 mmL/D ratio: : 23			
Extrusion	Nominal Value	Unit	
Drying Temperature	100 - 110	°C	
Drying Time	1.0 - 2.0	hr	
Cylinder Zone 1 Temp.	190 - 200	°C	
Cylinder Zone 2 Temp.	195 - 210	°C	
Cylinder Zone 3 Temp.	200 - 215	°C	
Cylinder Zone 4 Temp.	200 - 220	°C	
Die Temperature	190 - 210	°C	
Extrusion instructions			
Extruder Speed: 40rpmExtrusion Compression Ratio: 2:1 to 3:1Extrusion L/D Ratio: 25:1 to 30:1			
NOTE			
1.	C mould		
2.	10°C /min		
3.	Temperature at which MFI = 10 g/10 min @ 21.6 kg		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT