# **NEFTEKHIM PP 4345S**

### Polypropylene Copolymer

Nizhnekamskneftekhim Inc.

#### Message:

Product obtained by copolymerization of propylene and ethylene in presence of complex metalorganic catalysts.

It incorporates increased long-term thermal stability, thermal-oxidative degradation resistance when PP is produced, processed and PP-made articles are exploited, improved optical properties, improved antistatic properties to produce articles, improved rheology of melt, improved glossy surface of articles, easier demolding.

Application: high-speed jet molding, high-quality packaging, transparent containers and covers.

Technical requirements: TU 2211-136-05766801-2006

General Information					
Additive	Antistatic				
Features	Antistatic				
	Controlled Rheology				
	Copolymer				
	Good Mold Release				
	Good Thermal Stability				
	High Gloss				
	Opticals				
	Oxidation Resistant				
Uses	Containers				
	Packaging				
	Protective Coverings				
Forms	Pellets				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	0.900	g/cm³			
Apparent Density	0.48 to 0.60	g/cm³			
Melt Mass-Flow Rate (MFR) (230°C/2.16					
kg)	35 to 45	g/10 min	ASTM D1238		
Ash Content	0.025 to 0.050	%			
Thermal Creep Temperature <sup>1</sup>	70 to 80	°C			
Thermal-oxidative Deterioration (150°C)	15.0	day			
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale)	75 to 82				
Mechanical	Nominal Value	Unit	Test Method		
Flexural Modulus	950	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (23°C)	45	J/m	ASTM D256		

Thermal	Nominal Value	Unit	
Vicat Softening Temperature <sup>2</sup>	130 to 138	°C	
NOTE			
1.	at load 0.46 H/mm²		
2	in liquid medium under for	2 10 H	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

