

Lupox® GP1000H

Polybutylene Terephthalate

LG Chem Ltd.

Message:

Description
High Flow, High Impact
Applications
Automotive(Connector)

General Information			
UL YellowCard	E248280-533890	E67171-248566	
Features	High Flow		
	High Impact Resistance		
Uses	Automotive Applications		
	Connectors		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.29	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	50	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.2 to 2.0	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	47.1	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	> 100	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	1860	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 3.20 mm)	65.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.40 mm)	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	57.0	°C	ASTM D648
Peak Melting Temperature	223	°C	ASTM D3418
RTI Elec	140	°C	UL 746
RTI Imp	130	°C	UL 746
RTI Str	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257
Dielectric Strength (1.00 mm)	23	kV/mm	ASTM D149
Arc Resistance	PLC 5		ASTM D495
Comparative Tracking Index (CTI) ⁵	PLC 0		UL 746

Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.710 mm	HB		
1.50 mm	HB		
3.30 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	230 to 235	°C	
Middle Temperature	235 to 240	°C	
Front Temperature	240 to 245	°C	
Nozzle Temperature	240 to 250	°C	
Processing (Melt) Temp	240 to 250	°C	
Mold Temperature	40.0 to 80.0	°C	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		
5.	Solution A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

