Smoothblend® PC-1302

Polycarbonate

Colour Image Plastic Compound Sdn. Bhd. (CIPC)

Message:

Smoothblend® PC-1302 is a wear resistance polycarbonate compound offering superb lubricity by incorporating PTFE and carbon fiber. It is developed for applications demanding stringent wear resistant and low friction performance.

General Information				
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight			
Additive	PTFE Lubricant (15%)			
Features	Good Chemical Resistance			
	Good Thermal Stability			
	Good Wear Resistance			
	Low Friction			
	Lubricated			
Uses	Automotive Applications			
	Bushings			
	Engineering Parts			
	Gears			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.55	g/cm³	ASTM D792	
Molding Shrinkage - Flow (3.20 mm)	0.10 to 0.30	%	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	115	МРа	ASTM D638	
Tensile Elongation (Break)	2.0	%	ASTM D638	
Flexural Modulus	8610	МРа	ASTM D790	
Flexural Strength	180	МРа	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C)	190	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (1.8 MPa, Unannealed, 4.00 mm)	145	°C	ASTM D648	
Flammability	Nominal Value		Test Method	
Flame Rating (1.60 mm)	НВ		UL 94	
Injection	Nominal Value	Unit		
Drying Temperature	120	°C		
Drying Time	4.0 to 6.0	hr		

Rear Temperature	275 to 280	°C	
Middle Temperature	280 to 285	°C	
Front Temperature	285 to 290	°C	
Nozzle Temperature	290 to 295	°C	
Processing (Melt) Temp	275 to 300	°C	
Mold Temperature	85.0 to 110	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

