

Novalloy-A A2606

Acrylonitrile Butadiene Styrene + Nylon
PlastxWorld Inc.

Message:

Novalloy-A A2606 is an acrylonitrile butadiene styrene nylon (ABS nylon) material. This product is available in the Asia-Pacific region. The main characteristics of Novalloy-A A2606 are: flame retardant/rated flame.

General Information				
UL YellowCard		E47773-239580		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.30	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.10 - 0.50	--	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.60	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	116	115		ISO 2039-2
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (Yield)	120	95.0	MPa	ISO 527-2
Flexural Modulus	6800	5500	MPa	ISO 178
Flexural Stress	170	135	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	11	--	kJ/m ²	ISO 179/1eA
23°C	16	18	kJ/m ²	ISO 179/1eA
Notched Izod Impact				ASTM D256
-30°C, 6.40 mm	110	--	J/m	ASTM D256
23°C, 6.40 mm	160	190	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, unannealed, 6.40mm	215	210	°C	ASTM D648
0.45 MPa, not annealed	215	210	°C	ISO 75-2/B
1.8 MPa, unannealed, 6.40mm	195	180	°C	ASTM D648
1.8 MPa, not annealed	185	170	°C	ISO 75-2/A
Linear thermal expansion coefficient				ISO 11359-2
Flow	3.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral	1.0E-4	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method

Dielectric Strength (1.50 mm)	14	--	kV/mm	ASTM D149
Arc Resistance (3.00 mm)	92.0	--	sec	ASTM D495
Arc Resistance (3.00 mm)	PLC 6	--		ASTM D495
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating	HB	--		UL 94
Additional Information	Dry	Conditioned	Unit	
Moisture Content	--	0.70	%	
Injection	Dry	Unit		
Drying Temperature	90.0 - 100		°C	
Drying Time	4.0 - 5.0		hr	
Rear Temperature	180 - 210		°C	
Middle Temperature	230 - 250		°C	
Front Temperature	240 - 260		°C	
Nozzle Temperature	230 - 250		°C	
Mold Temperature	70.0 - 90.0		°C	
Back Pressure	10.0 - 20.0		MPa	
Screw Speed	50 - 80		rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT