

DeWAL DW 402

Ultra High Molecular Weight Polyethylene

DeWAL Industries

Message:

Skived Ultra High Molecular Weight Polyethylene film (UHMW)
UHMW has extremely high abrasion resistance, exceeding the abrasion resistance of steel. This coupled with broad chemical resistance and low coefficient of friction makes UHMW an extremely versatile engineering material for many severe service applications. Application examples include inner and outer surfaces for potable water, chemical, fuel and hydraulic hoses, bottom surfaces for skis and snow boards as well as linings for chutes to decrease friction and wear. Automotive weather stripping.

General Information			
Features	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Wear Resistance		
	High Tensile Strength		
	Low Friction		
	Ultra High Molecular Weight		
Uses	Abrasion Resistant Liners		
	Hose		
	Industrial Applications		
	Sporting Goods		
	Weatherstripping		
Forms	Film		
Physical	Nominal Value	Unit	
Density	0.930	g/cm ³	
Water Absorption (Saturation)	0.010	%	
Thickness	0.0762 to 2.36	mm	
Deformation ¹ (50°C)	6.0 to 8.0	%	
Core ID	7.62	cm	
Maximum Roll OD	356	mm	
Width ²	6.35 to 1220	mm	
Films	Nominal Value	Unit	Test Method
Tensile Strength - MD (Yield)	41.4	MPa	ASTM D882
Tensile Elongation - MD (Break)	300	%	ASTM D882
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Annealed)	95.0	°C	ISO 75-2/A
CLTE - Flow	2.0E-4	cm/cm/°C	
Thermal Conductivity (23°C)	0.063	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method

Dielectric Strength	39	kV/mm	ASTM D149
Dielectric Constant ³ (1 MHz)	2.30		ASTM D150
Dissipation Factor	4.0E-4		ASTM D150
NOTE			
1.	2000 psi, 6 hr		
2.	(increments of 1/16")		
3.	2H		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

