

SCANAMID 66 A12^ Q40

Polyamide 66

Polykemi AB

Message:

Mineral reinforced

General Information				
Filler / Reinforcement		Mineral,40% Filler by Weight		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.47	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.2	--	%	
Flow	1.2	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	80	--		ASTM D2240
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress	90.0	70.0	MPa	ISO 527-2
Tensile Strain (Break)	5.0	8.0	%	ISO 527-2
Flexural Modulus (23°C)	5000	3400	MPa	ISO 178
Flexural Stress	135	95.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-20°C	5.0	--	kJ/m ²	
23°C	8.0	11	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature ¹				
0.45 MPa, Unannealed	250	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	215	--	°C	ISO 75-2/A
Vicat Softening Temperature	> 230	--	°C	ISO 306/B50
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
Glow Wire Ignition Temperature (2.00 mm)	650	--	°C	IEC 60695-2-13
NOTE				
1.	120°C/hr			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT