

LNP™ THERMOCOMP™ UF007SXC

compound

Polyphthalamide

SABIC Innovative Plastics Europe

Message:

LNP THERMOCOMP UF007SXC is a compound based on Polyphthalamide resin containing Glass Fiber. Added features include : Heat Stabilized .

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.44	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.18	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11000	MPa	ISO 527-2/1
Tensile Stress (Break)	204	MPa	ISO 527-2/5
Tensile Strain (Break)	2.3	%	ISO 527-2/5
Flexural Modulus ¹	9100	MPa	ISO 178
Flexural Stress	280	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	11	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	50	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	258	°C	ISO 75-2/Af
CLTE			ISO 11359-2
Flow : 23 to 60°C	2.4E-5	cm/cm/°C	
Transverse : 23 to 60°C	5.8E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15	%	
Rear Temperature	310 to 321	°C	
Middle Temperature	316 to 327	°C	
Front Temperature	327 to 338	°C	
Processing (Melt) Temp	316 to 332	°C	

Mold Temperature	149 to 171	°C
Back Pressure	0.172 to 0.344	MPa
Screw Speed	30 to 60	rpm

NOTE		
1.	2.0 mm/min	
2.	80*10*4	
3.	80*10*4	
4.	80*10*4 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT