

# INLUBE POMCGF10TF15

Acetal (POM) Copolymer

Infinity LTL Engineered Compounds

Message:

Inlube PTFE, silicone, MoS2 and graphite internally lubricated compounds

Offered in all Infinity base resins and can be combined with reinforcements and process additives

Provide reduced coefficient of friction and low wear, including enhanced mechanical and thermal properties

| General Information                                     |                                  |                    |             |
|---|----------------------------------|--------------------|-------------|
| Filler / Reinforcement                                  | Glass Fiber,10% Filler by Weight |                    |             |
| Additive  | PTFE Lubricant (15%)             |                    |             |
| Features  | Good Wear Resistance             |                    |             |
|   | Low Friction                     |                    |             |
|   | Lubricated                       |                    |             |
| Physical  | Nominal Value                    | Unit               | Test Method |
| Specific Gravity  | 1.55                             | g/cm <sup>3</sup>  | ASTM D792   |
| Specific Volume   | 0.647                            | cm <sup>3</sup> /g |             |
| Molding Shrinkage - Flow                                | 0.90 to 1.1                      | %                  | ASTM D955   |
| Water Absorption (24 hr)                                | 0.30                             | %                  | ASTM D570   |
| Mechanical  | Nominal Value                    | Unit               | Test Method |
| Tensile Strength (Yield)                                | 75.8                             | MPa                | ASTM D638   |
| Tensile Elongation (Yield)                              | 4.0 to 7.0                       | %                  | ASTM D638   |
| Flexural Modulus  | 4140                             | MPa                | ASTM D790   |
| Flexural Strength                                       | 110                              | MPa                | ASTM D790   |
| Impact  | Nominal Value                    | Unit               | Test Method |
| Notched Izod Impact (3.18 mm)                           | 75                               | J/m                | ASTM D256   |
| Unnotched Izod Impact (3.18 mm)                         | 530                              | J/m                | ASTM D256   |
| Thermal   | Nominal Value                    | Unit               | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 143                              | °C                 | ASTM D648   |
| CLTE - Flow   | 7.2E-6                           | cm/cm/°C           | ASTM D696   |
| Electrical  | Nominal Value                    | Unit               | Test Method |
| Surface Resistivity                                     | 1.0E+16                          | ohms               | ASTM D257   |
| Flammability  | Nominal Value                    | Unit               | Test Method |
| Flame Rating (1.59 mm)                                  | HB                               |                    | UL 94       |
| Injection   | Nominal Value                    | Unit               |             |
| Drying Temperature                                      | 82.2                             | °C                 |             |
| Drying Time   | 4.0                              | hr                 |             |
| Processing (Melt) Temp                                  | 191 to 210                       | °C                 |             |

|                  |                |     |
|------------------|----------------|-----|
| Mold Temperature | 93.3           | °C  |
| Back Pressure    | 0.345 to 0.689 | MPa |
| Screw Speed      | 30 to 60       | rpm |
| Vent Depth       | 0.013 to 0.025 | mm  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

