

# Sylvin 7833-70 Natural

Polyvinyl Chloride  
Sylvin Technologies Incorporated

Message:  
Sylvin 7833-70 Natural Is A Vinyl Compound Formulated For Electrical Molding Applications.

General Information			
UL YellowCard	E86418-252037		
Uses	Electrical/Electronic Applications		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	70		ASTM D2240
Shaw A, 10 seconds	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	11.0	MPa	ASTM D638
Tensile Elongation (Break)	380	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	41.2	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Melting Temperature	160 - 171	°C	
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT