

Grilon® BM-30/2

Polyamide 6

EMS-GRIVORY

Message:

Grilon® BM-30/2 is a Polyamide 6 (Nylon 6) material filled with 30% mineral. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Grilon® BM-30/2 are:

- Flame Rated
- RoHS Compliant

Typical applications include:

- Automotive
- Consumer Goods
- Engineering/Industrial Parts
- Industrial Applications
- Tools

General Information				
UL YellowCard		E53898-243870	E132701-237886	
Filler / Reinforcement		Mineral,30% Filler by Weight		
Uses		Automotive Applications		
		Automotive Interior Parts		
		Consumer Applications		
		Engineering Parts		
		Industrial Applications		
		Power/Other Tools		
RoHS Compliance		RoHS Compliant		
Forms		Granules		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.80	--	%	
Flow	0.80	--	%	
Water Absorption				ISO 62
Saturation, 23°C	7.0	--	%	
Equilibrium, 23°C, 50% RH	2.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	180	75.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	5000	1700	MPa	ISO 527-2
Tensile Stress (Yield)	90.0	50.0	MPa	ISO 527-2
Tensile Strain (Yield)	5.0	25	%	ISO 527-2

Nominal Tensile Strain at Break	15	> 50	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	4.0	4.0	kJ/m ²	
23°C	7.0	12	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	90	130	kJ/m ²	
23°C	130	150	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	65.0	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	50.0	--	°C	ISO 75-2/C
Continuous Use Temperature				Internal Method
-- ¹	90.0 to 110	--	°C	
-- ²	160	--	°C	
Melting Temperature ³	222	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	9.0E-5	--	cm/cm/°C	
Transverse	9.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+14	1.0E+13	ohms · cm	IEC 60093
Electric Strength	34	31	kV/mm	IEC 60243-1
Comparative Tracking Index	--	550	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA 6, MH, 18-060, MD 30	--		ISO 1874
NOTE				
1.	Long Term			
2.	Short Term			
3.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

