

LEXAN™ SLX2432T resin

Polycarbonate
SABIC Innovative Plastics

Message:
Medium viscosity PC copolymer with enhanced UV stabilization and added release agent. V2 rated. Available in transparent and tinted colors.

General Information			
Additive	demoulding		
Features	Copolymer		
	Good UV resistance		
	Medium viscosity		
RoHS Compliance	RoHS compliance		
Appearance	Available colors		
	Clear/transparent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	9.00	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Water Absorption			
24 hr	0.12	%	ASTM D570
Saturated, 23°C	0.25	%	ISO 62
Equilibrium, 23°C, 50% RH	0.17	%	ISO 62
Outdoor Suitability	f1		UL 746C
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2550	MPa	ASTM D638
--	2550	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	67.0	MPa	ASTM D638
Yield	65.0	MPa	ISO 527-2/50
Fracture ³	72.0	MPa	ASTM D638
Fracture	69.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	6.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/50

Fracture ⁵	110	%	ASTM D638
Fracture	110	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2500	MPa	ASTM D790
-- ⁷	2500	MPa	ISO 178
Flexural Stress			
--	105	MPa	ISO 178
Yield, 50.0mm span ⁸	105	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	15	kJ/m ²	ISO 179/1eA
23°C	30	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰ (23°C)	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	98	J/m	ASTM D256
23°C	700	J/m	ASTM D256
-30°C ¹¹	10	kJ/m ²	ISO 180/1A
23°C ¹²	25	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	2600	J/m	ASTM D4812
23°C ¹³	No Break		ISO 180/1U
Instrumented Dart Impact			ASTM D3763
-40°C, Total Energy	85.0	J	ASTM D3763
23°C, Total Energy	77.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	130	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ¹⁴	130	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	118	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁵	116	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	135	°C	ASTM D1525, ISO 306/B50 10 ¹⁶
--	137	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	6.7E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	6.5E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-2		UL 94
Glow Wire Flammability Index (1.60 mm)	960	°C	IEC 60695-2-12
Oxygen Index	38	%	ISO 4589-2

Optical	Nominal Value	Unit	Test Method
Refractive Index	1.590		ASTM D542
Transmittance (2540 μm)	84.0	%	ASTM D1003
Haze (2540 μm)	0.80	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	255 - 280	°C	
Middle Temperature	265 - 290	°C	
Front Temperature	280 - 300	°C	
Nozzle Temperature	275 - 295	°C	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	70.0 - 95.0	°C	
Back Pressure	0.300 - 0.700	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.025 - 0.076	mm	
NOTE			
1.	50 mm/min		
2.	Type 1, 50mm/min		
3.	Type 1, 50mm/min		
4.	Type 1, 50mm/min		
5.	Type 1, 50mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*3 sp=62mm		
10.	80*10*3 sp=62mm		
11.	80*10*3		
12.	80*10*3		
13.	80*10*3		
14.	80*10*4 mm		
15.	80*10*4 mm		
16.	标准 B (120°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

