

TEDUR® L 9116-1

Polyphenylene Sulfide
ALBIS PLASTIC GmbH

Message:

TEDUR® L 9116-1 is a Polyphenylene Sulfide (PPS) product filled with 60% glass fiber. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of TEDUR® L 9116-1 include automotive and engineering/industrial parts.

Characteristics include:

- Flame Rated
- REACH Compliant
- RoHS Compliant
- Good Toughness
- High Stiffness

General Information			
Filler / Reinforcement	Glass Fiber,60% Filler by Weight		
Features	High Stiffness		
	Low Warpage		
	Ultra High Toughness		
Uses	Automotive Applications		
	Machine/Mechanical Parts		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.90	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	22000	MPa	ISO 527-2
Tensile Stress	140	MPa	ISO 527-2
Tensile Strain (Break)	0.90	%	ISO 527-2
Flexural Modulus	20000	MPa	ISO 178
Flexural Stress	220	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	25	kJ/m ²	ISO 179/1eU
Unnotched Izod Impact Strength	22	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	272	°C	ISO 75-2/A
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-0		

1.50 mm	V-0		
3.00 mm	V-0		
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	130 to 140	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	320 to 340	°C	
Mold Temperature	> 140	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

