

GPPC SAN D-20

Styrene Acrylonitrile
GPPC Chemical Co., Ltd.

Message:

GPPC SAN D-20 is a Styrene Acrylonitrile (SAN) material. It is available in Asia Pacific or North America for injection molding.
Important attributes of GPPC SAN D-20 are:
Flame Rated
Heat Resistant

General Information			
UL YellowCard	E88637-252445		
Features	High Heat Resistance		
Agency Ratings	CSA LS103112		
UL File Number	E88637		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			
200°C/5.0 kg	1.5	g/10 min	ASTM D1238
220°C/10.0 kg	15	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	82		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.18 mm)	76.5	MPa	ASTM D638
Flexural Modulus ² (3.18 mm)	3630	MPa	ASTM D790
Flexural Strength ³ (3.18 mm)	123	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
3.18 mm	20	J/m	
6.35 mm	19	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 12.7 mm)	95.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.59 mm	HB		
3.18 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	85.0 to 100	°C	
Processing (Melt) Temp	200 to 250	°C	
Mold Temperature	40.0 to 80.0	°C	

NOTE	
1.	50 mm/min
2.	15 mm/min
3.	15 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT