

RTP 1003 FR A

Polybutylene Terephthalate

RTP Company

Message:

Glass Fiber - Flame Retardant - UL94 V-0

General Information			
UL YellowCard	E84658-251409		
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Features	Flame retardancy		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.56	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.070	%	ASTM D570
Moisture Content	0.030	%	
Primary Additive	20	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8270	MPa	ASTM D638
Tensile Strength	110	MPa	ASTM D638
Tensile Elongation (Yield)	3.0 - 4.0	%	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Flexural Strength	165	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	530	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	210	°C	ASTM D648
1.8 MPa, not annealed	191	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+16	ohms · cm	ASTM D257
Dielectric Strength ¹ (in Oil)	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.50		ASTM D150
Dissipation Factor (1 MHz)	0.020		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94

Injection	Nominal Value	Unit
Drying Temperature	121	°C
Drying Time	4.0	hr
Dew Point	-28.9	°C
Processing (Melt) Temp	238 - 271	°C
Mold Temperature	79.4 - 107	°C
Injection Pressure	68.9 - 103	MPa

Injection instructions

Desiccant Type Dryer Required.

NOTE

1. Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

