

Sorona® 3015G BK001

RENEWABLY SOURCED™ THERMOPLASTIC POLYMER*

DuPont Performance Polymers

Message:

15% Glass Reinforced Polytrimethylene Terephthalate with Resin Made from Bio-PDO

General Information			
UL YellowCard	E41938-101123480		
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Processing Method	Injection Molding		
Part Marking Code (ISO 11469)	>PTT-GF15<		
Resin ID (ISO 1043)	PTT-GF15		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6200	MPa	ISO 527-2
Tensile Stress (Break)	110	MPa	ISO 527-2
Tensile Strain (Break)	2.3	%	ISO 527-2
Flexural Modulus	5700	MPa	ISO 178
Flexural Stress	170	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	25	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	185	°C	ISO 75-2/A
Melting Temperature ¹	227	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	3.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Electric Strength	36	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.00		
1 MHz	3.80		
Dissipation Factor			IEC 60250
100 Hz	1.5E-3		
1 MHz	0.017		
Comparative Tracking Index	275	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method

Flammability Classification			IEC 60695-11-10, -20
0.750 mm	HB		
1.50 mm	HB		
Oxygen Index	21	%	ISO 4589-2
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT