

Silopren® LSR 2030

Silicone Rubber, LSR

Momentive Performance Materials Inc.

Message:

Silopren LSR 2030 is a two-component liquid silicone rubber for injection molding processes. Because of its excellent processing properties, it can be considered for use in a wide range of applications.

Key Features and Benefits

Vulcanizates consisting of Silopren LSR 2030 typically are distinguished by the following properties:

- High thermal stability
- Excellent stability and flexibility at low temperatures
- Excellent biocompatibility
- Sterilizable with ethylene oxide, steam and gamma radiation
- Good rubber-like properties
- Long service life at dynamic stress
- High stability to ozone and ultraviolet light
- Outstanding resistance to aging
- Excellent dielectric behavior over a wide range of temperatures
- Not readily combustible, does not melt or drip
- Easily-pigmentable with LSR Color Pastes

Potential Applications

Because of its outstanding properties, Silopren LSR 2030 is an excellent candidate to consider for use in the following elastomeric articles:

- Sealing elements
- O-rings
- Stoppers
- Cable accessories

General Information	
Features	Biocompatible
	Ethylene Oxide Sterilizable
	Good Colorability
	Good Processability
	Good Stability
	Good Thermal Stability
	Good UV Resistance
	Low Temperature Flexibility
	Ozone Resistant
	Radiation Sterilizable
	Steam Sterilizable
Uses	Seals
Agency Ratings	BfR Food Contact, Unspecified Rating
	FDA 21 CFR 177.2600
	ISO 10993
	KTW Unspecified Rating
	USP Class VI
	WRAS Unspecified Rating

UL File Number	E205753		
Forms	Liquid		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	DIN 53479
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	31		DIN 53505
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	8.00	MPa	DIN 53504
Tensile Elongation (Break)	800	%	DIN 53504
Tear Strength ¹	18.0	kN/m	ASTM D624
Compression Set (175°C, 22 hr)	15	%	ISO 815
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Part A	Mix Ratio by Weight: 1.0		
Part B	Mix Ratio by Weight: 1.0		
Post Cure Time (200°C)	4.0	hr	
Additional Information	Nominal Value	Unit	Test Method
Vulcanization (175°C)	10.0	min	
Uncured Properties	Nominal Value	Unit	Test Method
Color			
-- ²	Translucent		
-- ³	Translucent		
Viscosity			DIN 53019
20°C ⁴	350	Pa·s	
20°C ⁵	350	Pa·s	
Pot Life (20°C)	4300	min	
NOTE			
1.	Die B		
2.	Part B		
3.	Part A		
4.	Part B		
5.	Part A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

