

# KEBAFLEX® E D 40.1

Thermoplastic Vulcanizate

BARLOG plastics GmbH

Message:

TPE-V, Shore D40

General Information			
Resin ID (ISO 1043)	TPE-V		
Physical	Nominal Value	Unit	Test Method
Density	0.950	g/cm <sup>3</sup>	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	16.0	MPa	ISO 527-2
Tensile Strain (Break)	620	%	ISO 527-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

