

TechnoMid A330

Polyamide 66
TechnoCompound GmbH

Message:

TechnoMid compounds are particularly suitable for technical applications due to their outstanding characteristics. The excellent sliding qualities and the favourable abrasion behaviour of TechnoMid compounds also permit their use in bearings.

TechnoMid compounds count among the technical thermoplastic compounds.

PA6 is made from caprolactam by means of hydrolytic polymerisation. The PA6.6 is produced by poly-condensation of hexa-ethylene diamine and adipic acid.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Good wear resistance		
Uses	Plug		
	Gear		
	Electrical/Electronic Applications		
	Electrical housing		
	Electrical appliances		
	Furniture		
	Household goods		
	Application in Automobile Field		
	Bearing		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7200	MPa	ISO 527-2
Additional Information			
Moisture Content, Infared 105°C, 15 min: 7200 MPa			
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 - 4.0	hr	
Processing (Melt) Temp	260 - 290	°C	
Mold Temperature	30.0 - 90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

