

Monprene® SP-12972 XRD2

Thermoplastic Elastomer

Teknor Apex Company

Message:

Monprene® SP-12972 XRD2 is a thermoplastic elastomer (TPE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is extrusion or injection molding.

Typical application areas include:

- Handle
- safety equipment
- packing
- kitchen utensils
- engineering/industrial accessories

General Information			
Uses	Safety equipment		
	Handle		
	Packaging		
	Kitchen utensils		
	Washer		
	Pipe fittings		
	Sporting goods		
	Shell		
	Stationery		
	Consumer goods application field		
Appearance	Opacity		
	Particle		
Forms			
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	11.7	MPa	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Injection	Nominal Value	Unit	
Rear Temperature	182 - 232	°C	

Middle Temperature	188 - 238	°C
Front Temperature	193 - 243	°C
Nozzle Temperature	199 - 249	°C
Processing (Melt) Temp	199 - 249	°C
Mold Temperature	35.0 - 48.9	°C
Injection Pressure	1.38 - 5.52	MPa
Injection Rate	Fast	
Back Pressure	0.172 - 0.689	MPa
Screw Speed	50 - 100	rpm
Cushion	3.81 - 25.4	mm

Injection instructions

无需干燥.但如果湿度过大,则将粒料在150°F (65°C)的温度下干燥2-4小时.

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	182 - 232	°C
Cylinder Zone 2 Temp.	188 - 238	°C
Cylinder Zone 3 Temp.	193 - 243	°C
Cylinder Zone 5 Temp.	199 - 249	°C
Die Temperature	199 - 249	°C

Extrusion instructions

螺杆转速30 - 100 rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT