

REPRO PP RT314

Polypropylene
Rondo Plast AB

Message:

PP 20% talcum reinforced

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Recycled Content	Yes		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow	0.90 to 1.2	%	
Flow	0.90 to 1.2	%	
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus (23°C)	1800	MPa	ISO 178
Flexural Stress	43.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	2.0	kJ/m ²	
23°C	4.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹ (1.8 MPa, Unannealed)	57.0	°C	ISO 75-2/A
Vicat Softening Temperature	80.0	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Ignition Temperature (2.00 mm)	750	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	180 to 220	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	40.0 to 110	MPa	
Injection Rate	Fast		
Back Pressure	1.00 to 2.00	MPa	
NOTE			
1.	120°C/hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

