

Altuglas® DRT

Polymethyl Methacrylate Acrylic
Altuglas International of Arkema Inc.

Message:

Altuglas® DRT is a Polymethyl Methacrylate Acrylic product. It is available in Asia Pacific or Europe. Primary characteristic: flame rated.

General Information			
Forms	Granules		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Specific Volume vs Temperature (ISO 11403-2)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1.15	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	0.80	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.20 to 0.80	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 50% RH)	0.36	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	46		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	38.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	40	%	ISO 527-2
Flexural Modulus (23°C)	1700	MPa	ISO 178
Flexural Stress (23°C)	62.0	MPa	ISO 178
Compressive Stress (23°C)	45.0	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.0	kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength (23°C)	60	kJ/m ²	ISO 179/2U
Notched Izod Impact Strength (23°C)	6.3	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	93.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	88.0	°C	ISO 75-2/A
Vicat Softening Temperature	100	°C	ISO 306/B
CLTE - Flow (-30 to 23°C)	1.0E-4	cm/cm/°C	ASTM D696
Specific Heat	2090	J/kg/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257

Volume Resistivity	> 1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	15	kV/mm	ASTM D149
Dielectric Constant (60 Hz)	3.90		ASTM D150
Dissipation Factor (1 MHz)	0.040		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index ¹	1.490		ISO 489
Transmittance	90.0	%	ASTM D1003
Haze	2.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	85.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	235 to 245	°C	
Mold Temperature	80.0 to 90.0	°C	
NOTE			

1. Method B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT