# ACLAR® 11A (2 mil)

## Polychlorotrifluoroethylene

Honeywell

### Message:

ACLAR® 11A (2 mil) is a polytrifluoroethylene (PCTFE) product. It can be processed by casting film and is available in North America, Europe or Asia Pacific. ACLAR® The application areas of 11A (2 mil) include electrical/electronic applications and industrial applications.

Features include:

Homopolymer

chemical resistance

| General Information      |                                    |            |             |
|--------------------------|------------------------------------|------------|-------------|
| Features                 | Homopolymer                        |            |             |
|                          | Good chemical resistance           |            |             |
|                          | Barrier resin                      |            |             |
|                          |                                    |            |             |
| Uses                     | Electrical/Electronic Applications |            |             |
|                          | Industrial application             |            |             |
| Forms                    | Particle                           |            |             |
| Processing Method        | cast film                          |            |             |
| Physical                 | Nominal Value                      | Unit       | Test Method |
| Density                  | 2.10                               | g/cm³      | ASTM D1505  |
| Films                    | Nominal Value                      | Unit       | Test Method |
| secant modulus           |                                    |            | ASTM D882   |
| MD : 51 μm               | 1170                               | MPa        | ASTM D882   |
| TD : 51 μm               | 1170                               | MPa        | ASTM D882   |
| Tensile Strength         |                                    |            | ASTM D882   |
| MD: Yield, 51 μm         | 52.0                               | MPa        | ASTM D882   |
| TD: Yield, 51 µm         | 42.0                               | MPa        | ASTM D882   |
| Tensile Elongation       |                                    |            | ASTM D882   |
| MD: Yield, 51 µm         | 200                                | %          | ASTM D882   |
| TD: Yield, 51 µm         | 250                                | %          | ASTM D882   |
| Water Vapor Transmission | 0.12                               | g/m²/24 hr | ASTM E96    |
| Thermal                  | Nominal Value                      | Unit       | Test Method |
| Thermal Conductivity     | 0.21                               | W/m/K      | ASTM C177   |
| Flammability             | Nominal Value                      | Unit       | Test Method |
| Oxygen Index (0.0508 mm) | 100                                | %          | ASTM D2863  |
| Optical                  | Nominal Value                      | Unit       | Test Method |
| Haze (50.8 μm)           | 1.0                                | %          | ASTM D1003  |

Yield, No Standard: 9.34 m²/kgTear Strength, ASTM D1004, Graves MD: 325 to 375 g/milTear Strength, ASTM D1004, Graves TD: 275 to 325 g/milCrystalline Melting Point, ASTM D4591: 211 °CDimensional Stability, ASTM D1204, MD: 5 to 10 %Dimensional Stability, ASTM D1204, TD: -5 to -10 %All film properties were tested as an average value.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

