

LNP™ THERMOCOMP™ PF008S compound

Polyamide 6

SABIC Innovative Plastics

Message:

LNP THERMOCOMP* PF008S is a compound based on Nylon 6 resin containing 40% Glass Fiber. Added features of this material include: Heat Stabilized.

Also known as: LNP* THERMOCOMP* Compound PF-1008 HS

Product reorder name: PF008S

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.47	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955, ISO 294-4
Flow : 24 hr	0.20 to 0.40	%	
Across Flow : 24 hr	0.60 to 0.80	%	
Water Absorption			
24 hr, 50% RH	0.98	%	ASTM D570
Equilibrium, 23°C, 50% RH	1.3	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	12700	MPa	ASTM D638
--	13000	MPa	ISO 527-2/1
Tensile Strength			
Break	184	MPa	ASTM D638
Break	186	MPa	ISO 527-2
Tensile Elongation (Break)	3.3	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	9260	MPa	ASTM D790
--	9530	MPa	ISO 178
Flexural Strength			
--	279	MPa	ASTM D790
--	278	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	130	J/m	ASTM D256
23°C ²	18	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	92	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			

23°C, Energy at Peak Load	25.1	J	ASTM D3763
--	21.6	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	196	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	208	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	249 to 260	°C	
Middle Temperature	266 to 277	°C	
Front Temperature	277 to 288	°C	
Processing (Melt) Temp	266 to 277	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

