

ExxonMobil™ LDPE LD 615BA

Low Density Polyethylene Resin

ExxonMobil Chemical

Message:

LD 615BA is a low density polyethylene grade with medium fluidity, which is characterized by high hardness and good toughness.

General Information			
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	45		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	150	MPa	ISO 527-2/1A/1
Tensile Stress (100% Strain)	9.20	MPa	ISO 527-2/1A/50
Tensile Strain (Break)	> 100	%	ISO 527-2/1A/50
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	86.0	°C	ISO 306
Legal statement			

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

