

Multi-Flex® TPE A2504 LC

Thermoplastic Elastomer
Multibase, A Dow Corning Company

Message:

Multi-Flex® TPE A2504 LC is a Thermoplastic Elastomer (TPE) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

General Information			
Features	Low Compression Set		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.30	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	23		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	4.67	MPa	ASTM D412
Tensile Elongation (Break)	720	%	ASTM D412
Tear Strength	12.6	kN/m	ASTM D624
Injection	Nominal Value	Unit	
Drying Temperature	65.6	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	185	°C	
Middle Temperature	188	°C	
Front Temperature	193	°C	
Nozzle Temperature	193	°C	
Processing (Melt) Temp	193	°C	
Mold Temperature	26.7 to 43.3	°C	
Injection Rate	Moderate-Fast		
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	160	°C	
Cylinder Zone 3 Temp.	188	°C	
Cylinder Zone 5 Temp.	210	°C	
Melt Temperature	204	°C	
Die Temperature	213	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

