

apilon 52c® C PC ESC 64

Thermoplastic Polyurethane Elastomer (PC Based)

API SpA

Message:

The wide range of APILON52 C products consisting exclusively of aromatic thermoplastic polyurethanes is equipped to meet most market demands. The APILON52 C famiy is organized in different chemical types, designed to provide a physical/ chemical performance corresponding to the specific needs of different uses in the FOOTWEAR, CLOTHING, LEATHER GOODS AND FURNISHINGS industries.

POLYCARBONATES - These are "TOP-CLASS" products used to manufacture items that cannot have chemical and mechanical performance compromises, and that must always guarantee the best possible result.

General Information			
Features	High Rigidity		
	Hydrolysis Resistant		
Uses	Footwear		
	Furniture		
	Sporting Goods		
Physical	Nominal Value	Unit	Test Method
Solution Viscosity ¹	4000 to 20000	mPa · s	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	64		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	45.0	MPa	
100% Strain	20.0	MPa	
300% Strain	33.0	MPa	
Tensile Elongation (Break)	500	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ²	200	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Melting Temperature ³	190 to 210	°C	
NOTE			
1.	20% in DMF		
2.	Without Notch		
3.	Kofler		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

