

LNP™ LUBRICOMP™ DFP36 compound

Polycarbonate

SABIC Innovative Plastics

Message:

LNP LUBRICOMP DFP36 is a compound based on Polycarbonate resin containing Glass Fiber, PTFE, Silicone.

Also known as: LNP* LUBRICOMP* Compound DFL-4536

Product reorder name: DFP36

General Information			
UL YellowCard	E45329-101344674		
Filler / Reinforcement	Glass fiber reinforced material		
Additive	PTFE silicone lubricant		
Features	Lubrication		
RoHS Compliance	RoHS compliance		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7900	MPa	ISO 527-2/1
Tensile Stress (Break)	98.0	MPa	ISO 527-2/5
Tensile Strain (Break)	2.2	%	ISO 527-2/5
Flexural Modulus ¹	5200	MPa	ISO 178
Flexural Stress	127	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ² (23°C)	13	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³			
0.45 MPa, unannealed, 64.0mm span	145	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 64.0mm span	140	°C	ISO 75-2/Af
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 60°C	2.2E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 60°C	5.1E-5	cm/cm/°C	ISO 11359-2
NOTE			
1.	2.0 mm/min		
2.	80*10*4		
3.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

