

SD POLYCA™ LR8061V-F10

Polycarbonate

Sumika Styron Polycarbonate Limited

Message:

Our light reflective products have high light reflectivity and good ignition resistant property, based on our excellent compounding technology. These grades are used for light reflective parts in LCD displays.

General Information			
UL YellowCard	E123529-271913		
Additive	Flame retardancy		
Features	High reflectivity		
	Flame retardant		
	Flame retardancy		
Uses	LCD application		
	Electrical housing		
	Sheet		
Part Marking Code	>PC FR(76)		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183
Molding Shrinkage			ASTM D955
Flow	0.50 - 0.70	%	ASTM D955
Transverse flow	0.50 - 0.70	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.18	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	114		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	60.0	MPa	ASTM D638
--	64.0	MPa	ISO 527-2
Tensile Elongation (Break)	5.0	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	3940	MPa	ASTM D790
--	4100	MPa	ISO 178
Flexural Strength			
--	92.0	MPa	ASTM D790
--	99.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m ²	ISO 179

Notched Izod Impact (23°C)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, not annealed	130	°C	ASTM D648
1.8 MPa, not annealed	135	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.0 mm	V-0		UL 94
3.0 mm	V-0		UL 94
Optical	Nominal Value		Test Method
Refractive Index ¹	89.00		Internal method
NOTE			

1. Thickness: 1 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

