

Tecomid® NA40 KG30 NL 0B

Polyamide 66

Eurotec Engineering Plastics

Message:

PA6.6, 30% glass fiber/glass bead reinforced, natural

General Information			
Filler / Reinforcement	Glass Beads \Glass Fiber, 30% Filler by Weight		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PA6.6 (GF+GB)30		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Molding Shrinkage			Internal method
Vertical flow direction	1.1	%	Internal method
Flow direction	0.40	%	Internal method
Water Absorption (Equilibrium, 23°C, 50% RH)	1.9	%	ISO 62
Moisture Content		%	ISO 960
Back Pressure	Low		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	7500	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	150	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	7.0	kJ/m ²	ISO 180/1A
23°C	8.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	50	kJ/m ²	ISO 180/1U
23°C	55	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	260	°C	ISO 75-2/B
1.8 MPa, not annealed	250	°C	ISO 75-2/A
Vicat Softening Temperature	250	°C	ISO 306/B
Melting Temperature ¹	262	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Comparative Tracking Index (Solution A)	500	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	HB		UL 94
1.60 mm	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 - 4.0	hr	
Hopper Temperature	60.0 - 80.0	°C	
Processing (Melt) Temp	270 - 300	°C	
Mold Temperature	70.0 - 110	°C	
Injection Rate	Fast		
Holding Pressure	50.0 - 100	MPa	
Injection instructions			
Pre-drying is not necessary for materials in moisture proof closed bags.			
NOTE			
1.	10 K/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

