# Moplen PP567P

### Polypropylene Homopolymer LyondellBasell Industries

#### Message:

Moplen PP567P is used in extrusion applications. It has a very narrow molecular weight distribution and it is formulated with an anti-gasfading stabilisation package. Moplen PP567P is used in the production of continuous filaments. Typical applications are high-tenacity yarns (HTY), continuous filaments (CF), bulk continuous filaments (BCF) and spunbond nonwovens. For regulatory information please refer to Moplen PP567P Product Stewardship Bulletin (PSB).

General Information					
Additive	Anti-gas fading	Anti-gas fading			
Features	Gas-fading Resistant				
	Homopolymer				
	Narrow Molecular Weight Distribution				
Uses	BCF Multifilaments				
	Filaments				
	Spunbond Nonwovens				
	Yarn				
Forms	Pellets				
Processing Method	Extrusion				
	Fiber (Spinning) Extrusion				
	Filament Extrusion				
Physical	Nominal Value	Unit	Test Method		
Melt Mass-Flow Rate (MFR)	18	g/10 min	ISO 1133		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Stress			ISO 527-2		
Yield	33.0	MPa			
Break	21.0	MPa			
Tensile Strain			ISO 527-2		
Yield	11	%			
Break	> 500	%			
Flexural Modulus	1300	MPa	ISO 178		
Impact	Nominal Value	Unit	Test Method		
Charpy Notched Impact Strength	5.0	kJ/m²	ISO 179		
Charpy Unnotched Impact Strength	150	kJ/m²	ISO 179		
Thermal	Nominal Value	Unit	Test Method		
Heat Deflection Temperature (0.45 MPa,					
Unannealed)	86.0	°C	ISO 75-2/B		

Vicat Softening Temperature					
	153	°C	ISO 306/A50		
	93.0	°C	ISO 306/B50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

