

NORYL™ HNA055 resin

Polyphenylene Ether + PS

SABIC Innovative Plastics

Message:

>PPE+PS-HI< Autoclavable engineering thermoplastic. Biocompatible per ISO10993 (color dependent).

General Information			
Features	High pressure heating resistance		
	Biocompatibility		
Agency Ratings	ISO 10993		
Processing Method	Injection molding		
Part Marking Code (ISO 11469)	>PPE+PS-HI		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/5.0 kg)	6.2	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/5.0 kg)	5.70	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.80	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.23	%	ISO 62
Equilibrium, 23°C, 50% RH	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	3250	MPa	ASTM D638
--	2410	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	67.9	MPa	ASTM D638
Yield	61.8	MPa	ISO 527-2/50
Fracture ³	55.5	MPa	ASTM D638
Fracture	57.6	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	4.8	%	ASTM D638
Yield	3.8	%	ISO 527-2/50
Fracture ⁵	16	%	ASTM D638
Fracture	13	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2540	MPa	ASTM D790
-- ⁷	2490	MPa	ISO 178
Flexural Stress			

--	107	MPa	ISO 178
Yield, 50.0mm span ⁸	101	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	27	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	140	J/m	ASTM D256
23°C	290	J/m	ASTM D256
-30°C ¹⁰	15	kJ/m ²	ISO 180/1A
23°C ¹¹	25	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	54.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	147	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	148	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	168	°C	ASTM D1525, ISO 306/B50 10 ¹³
--	169	°C	ISO 306/B120
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	8.7E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	9.3E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	104 - 110	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	30 - 70	%	
Rear Temperature	260 - 304	°C	
Middle Temperature	271 - 310	°C	
Front Temperature	282 - 316	°C	
Nozzle Temperature	293 - 316	°C	
Processing (Melt) Temp	293 - 316	°C	
Mold Temperature	76.7 - 104	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	20 - 100	rpm	
NOTE			
1.	5.0 mm/min		
2.	Type 1, 50mm/min		
3.	Type 1, 50mm/min		
4.	Type 1, 50mm/min		
5.	Type 1, 50mm/min		
6.	1.3 mm/min		

7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT