

ESTAPROP 1006

Polypropylene Homopolymer

Cossa Polimeri S.r.l.

Message:

ESTAPROP 1006 is a polypropylene homopolymer (PP Homopoly) product. It is available in Europe. Typical application areas are: electrical appliances.
Features include:
Flame Retardant
Good processability
Homopolymer

General Information			
Features	Low Halogen Content		
	Low smoke		
	Homopolymer		
	Workability, good		
	Flame retardancy		
Uses	Electrical appliances		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.920	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.7 - 2.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	25.0	MPa	ASTM D638
Tensile Elongation (Yield)	50	%	ASTM D638
Flexural Modulus	1500	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	30	J/m	ASTM D256
23°C	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	150	°C	ASTM D1525 ¹
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	190 - 210	°C	
Mold Temperature	40.0 - 60.0	°C	
Injection Rate	Slow		
Injection instructions			
Injection Pressure: Low			

NOTE

1. 压力1 (10N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

