

Precision Polymer V75M

Fluoroelastomer

Precision Polymer Engineering Ltd.

Message:

Brown Fluoroelastomer Rubber, 70-80 IRHD. Copolymer of vinylidene fluoride and hexafluoropropylene. To meet ASTM D2000 line call-out:- M2HK710, A1-10, B37, B38, EF31, EO78, F15, Z1, Z2. Z1 = comp-set 30% max. Z2 = brown. ASTM designation = FKM. ISO designation = FPM.
Excellent resistance to oils, fuels and hydraulic fluids at high temperatures.

General Information			
Features	Fuel resistance		
	Heat resistance, high		
	Oil resistance		
Agency Ratings	ASTM D 2000		
Appearance	Brown		
Hardness	Nominal Value		Test Method
IRHD Hardness	75		ASTM D1415, ISO 48
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	10.0	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	180	%	ASTM D412, ISO 37
Compression Set			
200°C, 24 hr	30	%	ASTM D395B
200°C, 24 hr ¹	30	%	ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (250°C, 72 hr)	-25	%	ASTM D412, ISO 37
Change in Ultimate Elongation in Air (250°C, 72 hr)	-25	%	ASTM D412, ISO 37
Change in IRHD Hardness in Air (250°C, 72 hr)	10		ASTM D573, ISO 188
Thermal	Nominal Value	Unit	
Maximum Operating Temperature	200	°C	
Additional Information			
Minimum Operating Temperature: -20°C (-4°F)			
NOTE			
1.	Type B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

