

TARFLON™ NEO AG2530

Polycarbonate
Idemitsu Kosan Co., Ltd.

Message:
High strength

General Information			
Features	Copolymer		
	High Strength		
UL File Number	E48268		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	5.00	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow : 2.00 mm	0.60 to 0.80	%	
Flow : 2.00 mm	0.60 to 0.80	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Nominal Tensile Strain at Break	90	%	ISO 527-2
Flexural Modulus	2100	MPa	ISO 178
Flexural Stress	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	75	kJ/m ²	
0°C	85	kJ/m ²	
23°C	95	kJ/m ²	
Notched Izod Impact			ASTM D256
-30°C	900	J/m	
0°C	1000	J/m	
23°C	1100	J/m	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	128	°C	ISO 75-2/A
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value	Test Method	
Flame Rating (0.500 to 3.00 mm)	V-2	UL 94	

Additional Information	Nominal Value	
ISO Shortname	>PC<	
Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	5.0 to 8.0	hr
Rear Temperature	270 to 310	°C
Middle Temperature	270 to 310	°C
Front Temperature	270 to 310	°C
Mold Temperature	80.0 to 120	°C
NOTE		
1.	24h	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

