

Fluoroplex MB 555 - GML

Polytetrafluoroethylene

UNIFLON

Message:

Fluoroplex MB 555-GML is a polytetrafluoroethylene (PTFE) product, which contains 55% bronze filler. It can be processed by sintering or injection molding and is available in North America or Latin America. The main characteristics are: lubrication.

General Information	
Filler / Reinforcement	Bronze filler, 55% filler by weight
Additive	Molybdenum disulfide lubricant (5%)
Features	Low liquidity
Processing Method	Sintering Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	3.75 - 3.85	g/cm ³	Internal method
Contractility-Sintering	0.90 - 1.9	%	Internal method
Sintering Temperature - Maximum	360	°C	

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	69 - 74		Internal method

Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	16.0	MPa	Internal method
Tensile Elongation (Break)	80	%	Internal method

Additional Information	Nominal Value	Unit
------------------------	---------------	------

Code: 010003901

Injection	Nominal Value	Unit
Mold Temperature	21.0 - 25.0	°C
Injection Pressure	49.0 - 58.8	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT