

DENYL 66 0037 H

Polyamide 66
Vamp Tech

Message:
PA 66, with elastomer, not Flame Retardant compound, good impact resistance.

General Information				
Features		Good Impact Resistance		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.11	--	g/cm ³	ASTM D792
Molding Shrinkage				ASTM D955
Flow	1.6	--	%	
Across Flow	1.6	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2300	--	MPa	ASTM D638
Tensile Strength				
Yield	60.0	42.0	MPa	ASTM D638
Yield	--	42.0	MPa	ISO 527-2
Tensile Elongation				
Yield	--	180	%	ASTM D638, ISO 527-2
Break	> 20	--	%	ASTM D638
Flexural Modulus	--	1000	MPa	ASTM D790, ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact Strength	13	--	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	No Break	--		ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	70.0	--	°C	ASTM D648A
Vicat Softening Temperature	215	--	°C	ASTM D1525 ¹
RTI Elec	100	--	°C	UL 746
RTI Imp	100	--	°C	UL 746
RTI Str	100	--	°C	UL 746
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (CTI)	600	--	V	UL 746
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	3.0		hr	

Processing (Melt) Temp	270	°C
Mold Temperature	80.0	°C
NOTE		
1.	Loading 2 (50 N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT