

LNP™ THERMOCOMP™ LF003 compound

Polyetheretherketone
SABIC Innovative Plastics

Message:

LNP THERMOCOMP LF003 is a compound based on Polyetheretherketone resin containing Glass Fiber.
Also known as: LNP* THERMOCOMP* Compound LF-1003
Product reorder name: LF003

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.80	%	ASTM D955
Transverse flow: 24 hours	1.0	%	ASTM D955
Vertical flow direction: 24 hours	1.0	%	ISO 294-4
Flow direction: 24 hours	0.79	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6930	MPa	ISO 527-2/1
Tensile Strength			
Yield	137	MPa	ASTM D638
Yield	125	MPa	ISO 527-2
Fracture	137	MPa	ASTM D638
Fracture	125	MPa	ISO 527-2
Tensile Elongation			
Yield	2.9	%	ASTM D638
Yield	2.4	%	ISO 527-2
Fracture	3.1	%	ASTM D638
Fracture	2.4	%	ISO 527-2
Flexural Modulus			
--	62700	MPa	ASTM D790
--	7000	MPa	ISO 178
Flexural Strength			
--	200	MPa	ASTM D790
--	209	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	53	J/m	ASTM D256
23°C ¹	6.6	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	850	J/m	ASTM D4812

23°C ²	54	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	14.6	J	ASTM D3763
--	3.10	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	329	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ³	325	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	259	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	244	°C	ISO 75-2/Af
Linear thermal expansion coefficient			
Flow: -40 to 40°C	4.9E-5	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	4.8E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	3.1E-5	cm/cm/°C	ASTM E831, ISO 11359-2
NOTE			
1.	80*10*4		
2.	80*10*4		
3.	80*10*4 mm		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

