

Iupiace® GV10

Polyphenylene Ether + PS

Mitsubishi Engineering-Plastics Corp

Message:

Iupiace® GV10 is a Polyphenylene Ether + PS (PPE+PS) material filled with 10% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding. Primary attribute of Iupiace® GV10: Flame Rated.

General Information			
UL YellowCard	E41179-232059		
Filler / Reinforcement	Glass Fiber, 10% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.15	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/2.16 kg)	6.50	cm ³ /10min	ISO 1133
Molding Shrinkage			
Across Flow : 3.20 mm	0.30 to 0.50	%	
Flow : 3.20 mm	0.20 to 0.40	%	
Water Absorption (Saturation, 23°C)	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4500	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	83.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.5	%	ISO 527-2
Flexural Modulus (23°C)	4400	MPa	ISO 178
Flexural Stress (23°C)	140	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	126	°C	ISO 75-2/B
1.8 MPa, Unannealed	120	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	4.5E-5	cm/cm/°C	
Transverse	7.5E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+15	ohms	IEC 60093
Volume Resistivity	3.0E+16	ohms · cm	IEC 60093
Comparative Tracking Index	200	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm)	V-1		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	100 to 120	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	260 to 290	°C
Middle Temperature	280 to 310	°C
Front Temperature	280 to 310	°C
Nozzle Temperature	270 to 310	°C
Mold Temperature	90.0 to 125	°C
Injection Pressure	20.0 to 150	MPa
Injection Rate	Moderate	
Screw Speed	60 to 150	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

