

4PROP® 9D02430 UV

Polypropylene Homopolymer
4Plas

Message:

4PROP 9D02430 UV is a MFI 4 30% Chemically Coupled Glass Fibre UV Stabilised Homopolymer Polypropylene

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	UV stabilizer		
Features	Chemical coupling		
	Homopolymer		
	Good UV resistance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	5500	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	80.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.5	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	45	kJ/m ²	ISO 179/1eU
23°C	55	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	10	kJ/m ²	ISO 180/1A
23°C	12	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	160	°C	ISO 75-2/B
1.8 MPa, not annealed	145	°C	ISO 75-2/A
Melting Temperature ¹	165	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	HB		UL 94

1.60 mm	HB	UL 94
Injection	Nominal Value	Unit
Processing (Melt) Temp	200 - 240	°C
Mold Temperature	20.0 - 50.0	°C
Injection Rate	Moderate	
Holding Pressure	40.0 - 80.0	MPa
Screw Speed	200	rpm
Injection instructions		
Feed Throat Temperature: 20 - 60 °CBack Pressure: Low		
NOTE		
1.	10 K/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT